

## Adhesive Summary Specifications

---

### Bedding Adhesive (TD5621):

600ml / 0.84kg sausage of Bostik, Non-Hazmat single part, Moisture Curing, Silyl Modified Polymer

Skin forming in 10 -15 minutes at 20 degrees C & 50% RH

Full cure in 24 to 36 hours

0.84kg per sq.metre, 76gr/sqft or 1.85lbs per 10.76sqft



### Caulking (TD5620 or Simson MSR Deck Caulk):

1 x 290ml tube of either:

Bostik, Non-Hazmat single part, Moisture Curing, Silyl Modified Polymer

Skin forming in 10 -15 minutes at 20 degrees C & 50% RH

Full cure in 24 to 36 hours

or

Simson MSR DC (Bostik subsidiary company) Non-Hazmat single part, Moisture Curing, Silyl Modified Polymer deck caulk

Skin forming in 10 minutes at 20 degrees C & 50% RH

Full cure in 24 hours

290ml tube fills 19ft of caulking seams



### Tongue & Groove Adhesive (TD5612 - Clear Stelmax and TD5612-B Black Stelmax)

Hazmat classification, Flammable - Tetrahydrofuran

Skin forms in 3 to 5 minutes depending on temperature. Full cure in 1 to 2 hours

1 x 135g tube = 92ft of tongue & groove seams.

